

IN THE CLAIMS

1-9 (Canceled)

10. (Currently Amended) A filter element for removing contaminants from gases, comprising a monolithic porous carbon structure, wherein the non-filled monolithic porous carbon structure is a single piece and is not granular and is not composed of granular carbons bound together by a binder and the walls of the carbon monolithic structure have continuous voids or pores through which liquid or vapours can pass, and wherein the carbon of said monolithic porous carbon structure is not bound to silica.

11. (Currently Amended) A filter element according to claim 10, wherein the non-filled monolithic porous carbon structure has a cell structure wherein the channel size is between about 100microns and 2000microns and the wall thickness is between about 100microns and 2000microns with an open area of between about 30 and 60%.

12. (Currently Amended) A filter element according to claim 10, wherein the non-filled monolithic porous carbon structure has a surface area of at least  $700\text{m}^2/\text{g}$ .

13. (Currently Amended) A filter element according to claim 11, wherein the non-filled monolithic porous carbon structure has a surface area of at least  $700\text{m}^2/\text{g}$ .

14. (Currently Amended) A filter element according to claim 10, wherein the non-filled monolithic porous carbon structure ~~carbon monolithic structure~~ has a surface area in excess of  $1000\text{m}^2/\text{g}$ .

15. (Currently Amended) A filter element according to claim 11, wherein the non-filled monolithic porous carbon structure ~~carbon monolithic structure~~ has a surface area in excess of  $1000\text{m}^2/\text{g}$ .

16. (Currently Amended) A filter element according to claim 10, wherein the non-filled monolithic porous carbon structure ~~carbon monolithic structure~~ has a length of about 1 to 10 cm.

17. (Currently Amended) A filter element according to claim 10, wherein the non-filled monolithic porous carbon structure ~~carbon monolithic structure~~ is produced by partially curing a phenolic resin to a solid, comminuting the partially cured resin, extruding the comminuted resin, sintering the extruded resin so as to produce a form-stable sintered product and carbonising the form-stable sintered product.

18. (Currently Amended) A filter element according to claim 11, wherein the non-filled monolithic porous carbon structure ~~carbon monolithic structure~~ is produced by partially curing a phenolic resin to a solid, comminuting the partially cured resin, extruding the comminuted resin, sintering the extruded resin so as to produce a form-stable sintered product and carbonising the form-stable sintered product.

19. (Previously presented) A filter element according to claim 10, comprising a plurality of filter elements wherein each of the filter elements is from about 1 to 3 cm in length separated from an adjacent filter element by a gap of about 0.5 to 1.5 cm.

20. (Currently Amended) An apparatus for the removal of contaminants from gases such as air, comprising a container containing (i) a filter element; (ii) a gas inlet for the container and (iii) a gas outlet for the container whereby gases can pass via the inlet through the filter element and out through the outlet and in which the filter element comprises a non-filled monolithic porous carbon structure which is a single piece and is not granular and is not composed of granular carbons bound together by a binder and the walls of the carbon monolithic structure have continuous voids or pores through which liquid or vapours can pass, and wherein the carbon of said monolithic porous carbon structure is not bound to silica.

21. (Currently Amended) Apparatus according to claim 20, wherein the non-filled monolithic porous carbon structure has a cell structure wherein the channel size is between about 100microns and 2000microns and the wall thickness is between about 100microns and 2000microns with an open area of between about 30 and 60%.

22. (Currently Amended) Apparatus according to claim 21, wherein the non-filled monolithic porous carbon structure has a surface area of at least  $700\text{m}^2/\text{g}$ .

23. (Currently Amended) Apparatus according to claim 20, wherein the non-filled monolithic porous carbon structure ~~carbon monolithic structure~~ has a surface area in excess of  $1000\text{m}^2/\text{g}$ .

24. (Currently Amended) Apparatus according to claim 21, wherein the non-filled monolithic porous carbon structure ~~carbon monolithic structure~~ has a surface area in excess of  $1000\text{m}^2/\text{g}$ .

25. (Previously presented) Apparatus according to claim 20, wherein there is a plurality of filter elements and wherein each of the filter elements is from about 1 to 3 cm in length and is separated from an adjacent filter element by a gap of about 0.5 to 1.5 cm.

26. (Previously presented) Apparatus according to claim 21, wherein there is a plurality of filter elements and wherein each of the filter elements is from about 1 to 3 cm in length and is separated from an adjacent filter element by a gap of about 0.5 to 1.5 cm.

27. (Currently Amended) Apparatus according to claim 20, wherein the non-filled carbon monolithic structure is produced by partially curing a phenolic resin to a solid, comminuting the partially cured resin, extruding the comminuted resin, sintering the extruded resin so as to produce a form-stable sintered product and carbonising the form-stable sintered product.

28. (Currently Amended) Apparatus according to claim 21, wherein the non-filled carbon monolithic structure is produced by partially curing a phenolic resin to a solid, comminuting the partially cured resin, extruding the comminuted resin, sintering the extruded resin so as to produce a form-stable sintered product and carbonising the form-stable sintered product.

29. (Previously Presented) Apparatus according to claim 20, further comprising a respirator.